

## Pigment preparations

## Abstract

5

Pigment preparations including as essential constituents

(A) from 60 to 90% by weight of at least one pigment,

10 (B) from 10 to 40% by weight of at least one nonionic  
surface-active additive based on polyethers, and

(C) from 0.1 to 10% by weight of at least one anionic  
surface-active additive based on sulfonates, sulfates,  
15 phoshonates or phosphates,

the sum total of the weight percentages not exceeding 100% by  
weight,

20 are prepared and used for pigmenting macromolecular organic and  
inorganic materials.

25

30

35

40

45